

电话: 86-552-3827158

安徽明怡硅业有限公司

Ming Yi Silicone Co., Ltd.

Tel: 86-552-3827158

安徽省蚌埠市高新区兴中路 985 号日月 Sunmoon industry park, 985 Xingzhong Road, Bengbu,

科技园 China 233000

传真: 86-552-3822922 Fax: 86-552-3822922

TDS of General purpose High temperature resistant silicone

This product is specially designed for the products working at high temperature. It is manufactured with special formula and process, without changing the unique cold resistance of silicone rubber and the excellent physical and mechanical properties, covering a wide range of applications. The three series are slightly different in the appearance: the common type is milk-white, translucent or white; the standard type is light yellow or maroon and the fumed type is light yellow. This product can be used at 250°C for a long time and can withstand an instant temperature of 300°C. It is applicable to production of various temperature resistant seals, rubber rolls and sealing joint strips, etc.

Typical Properties:

Category General purpose Appearance		Item						
		MY DI140	MY DI150	MY DI160	MY DI170	MY DI180		
		Ivory						
Vulcanization	Hardness Shore A	40±3	50±3	60±3	70±3	80±3		
	Tensile strength MPa≥	6.0	7.5	7.5	7.0	6.5		
	Elongation at break %≥	420	380	320	220	180		
	Breaking set %≤	7	8	8	8	7		
	Tear strength B KN/m≥	18	20	20	20	18		
Post-curing	Hardness Shore A	45±3	55±3	65±3	75±3	85±3		
	Tensile strength MPa≥	6.5	7.5	7.0	7.0	6.5		
	Elongation at break %≥	400	350	300	200	150		
	Tear strength B KN/m≥	16	18	18	18	16		
Specific density 25°C g/cm³		1.13±0.05	1.15±0.05	1.19±0.05	1.22±0.05	1.25±0.05		
Compression set 180*22h %≤		35	35	25	30	25		



安徽明怡硅业有限公司

Ming Yi Silicone Co., Ltd.

安徽省蚌埠市高新区兴中路 985 号日月

科技园

电话: 86-552-3827158

传真: 86-552-3822922

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

Property	Hardness	-5	-6	-4	5	6
variation	Tensile strength %	-45	-50	-50	-40	-25
percent during						
aging (250°C	Elongation %	-20	-15	-20	-35	-20
*72h)						

Physical data in the above table is for reference only.

Vulcanization condition: $175^{\circ}\text{C} \times 5\text{Min}$. Post-curing condition: $200^{\circ}\text{C} \times 4\text{h}$

Addition of curing agent: liquid 2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane: 0.65%.

Advantage:

- Excellent physical properties
- Being used at 250°C for a long time
- Withstanding an instant temperature of 300°C

Applications:

 Applicable to various high-temperature-resistant sealing elements, rubber rolls and sealing strips

Packing & Storage:

- 20kg/ carton lined with plastic bags or sheets.
- The products have a shelf life of 9 months from date of manufacture depending on the shore hardness if stored at room temperature in the originally sealed container.