


**TDS of MY120 Methyl phenyl vinyl silicone rubber**



p=0 or customized

High temperature vulcanized silicone rubber, especially suitable for extreme environment.

**Technical index:**

This value is a typical data, non product specification value

Test	Unit	Value
Appearance		colourless
Phenyl content ( Ph/Si )	%	5-40
molecular weight ( Mw )	10 <sup>4</sup>	40-80
specific gravity ( 25°C )		0.99-1.05
volatile ( 150°C/3h )	%	≤2

**Advantage:**

High and low temperature resistance, higher reliability in operation and performance

Adjustable modulus - design flexibility

Excellent cold resistance (low phenyl content)



安徽明怡硅业有限公司

**Ming Yi Silicone Co., Ltd.**

安徽省蚌埠市高新区兴中路 985 号日月科技园

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

电话: 86-552-3827158

Tel: 86-552-3827158

传真: 86-552-3822922

Fax: 86-552-3822922

---

Excellent resistance to ablation (medium and high phenyl content)

Excellent radiation resistance (high phenyl content)

**Packaging And Storage:**

25kg cardboard boxes (lined with plastic bags)

Shelf life is 1 year.